arXiv:1207.1152v1 [cond-mat.mtrl-sci] 5 Jul 2012

Disentanglement Induced Magnetoresistance in Organic Semiconductors

Wei Si, Yao Yao, Xiaoyuan Hou, and Chang-Qin Wu*
State Key Laboratory of Surface Physics and Department of Physics, Fudan University, Shanghai 200433, China

(Dated: July 6, 2012)

By considering explicitly the contribution of carrier's spin in various incoherent charge transfer (CT) process, we propose a fundamental mechanism for magnetoresistance in organic semiconductors. It is proven that the disentanglement between the carrier's spin and the local environment, accompanying the incoherent CT, contributes a reduction factor to the intermolecular CT rate. The entanglement is altered by the applied magnetic field, which leads to the magnetoresistance. Based on a hyperfine interaction model, we show the CT rate exhibits a general feature of a Lorenzian-shape saturation at large fields, together with an ultrasmall-field component. Furthermore, the ultrasmall-field component is shown to be a result of the coherent motion of carrier's spin, while the saturation behavior survives the loss of coherence. The magnetic-field dependence, as well as the obtained isotope effect, are in satisfying agreement with the experimental results [T.D. Nguyen *et al.*, Nature Materials **9**, 345 (2010)]. The mechanism also explains the diversity of magnetoresistance observed in various organic materials.

PACS numbers: 72.20.My, 72.80.Le, 31.30.Gs

Recently, a series of experiments have revealed the surprising long-range quantum coherence at picosecond timescales in the excitation energy transfer among the light-absorbing molecules in photosynthetic proteins [1]. It is further proposed that the the light-harvesting efficiency can be enhanced by the accompanying quantum entanglement [2], whose essential role is also supported by a theoretical analysis concluding that the entanglement could take effect for nonequilibrium systems even at room temperature [3]. These discoveries indicate that, the processes related to quantum coherence, such as quantum entanglement and disentanglement, which are previously thought to be fragile, could lead to new physical consequences in "natural" and molecular systems.

As a promising branch of molecular electronics, the organic thin-film devices have raised much attention due to their low cost, flexibility and ease of fabrication [4]. The microscopic process of charge transport and recombination is thought to be a series of charge transfer (CT) between molecules, or more abstractly, transport sites, under different conditions. For example, a single charge carrier on a specific site can hop onto a neighboring vacant site. Moreover, if the destination site is already occupied by an oppositely charged carrier, a singlet or triplet exciton will form. More complicated processes are expected such as the CT to and off a site with a long-lived triplet exciton, namely the triplet-polaron interaction. Due to both the amorphous morphology and the self-trapping effect brought about by the electron-lattice interaction, most of the CT processes are thought to be incoherent, and are well described by the CT rate. Various theories for the CT rate have been proposed for different situations, such as the Miller-Abrahams formula [5] and the Marcus formula [6]. These theories, in combination with the Gaussian disorder model, capture the electric-field and temperature dependence of mobility in a certain range successfully [7]. The discovery of the magnetoresistance (MR), together with the magneto-electroluminescence (MEL) [9, 10] in the organic thin film devices raises a new topic on the role of the carrier's spin in the CT processes. Novel physics is expected, which differs from that of the inorganic counterparts due to the coherence of the carrier's spin and the incoherence of charge transport in such systems [11, 12]. Based on the experiments under different operating conditions, a number of quantities are claimed to be modulated by magnetic field [13], including the charge carrier mobility [14], the inter-system crossing rate between singlet and triplet electron-hole pairs [15], and the recombination mobility [16]. It should be noted that, despite the diversity of the underlying processes, both the MR and MEL show surprising universality and similarity in a wide range of materials [17] and temperatures [18], which implies that a general understanding from the basic characteristics of the underlying CT processes is required.

In this Letter, we study explicitly the motion of the carrier's spin in the incoherent CT processes of organic semiconductors. We point out that a disentanglement process will accompany the incoherent CT, through which the CT rate is related to the entanglement between the carrier's spin and the local environment. This entanglement can be modulated by the applied magnetic field, which leads to the MR, which is a fundamental mechanism beyond the common "spin-selection" rules. By considering a hyperfine-interaction model and the hopping of a single carrier from a specific site to its neighboring vacant site, we calculated the magnetic-field dependence of the hopping rate, which shows a general feature of a Lorenzian-shape saturation at large fields, together with an ultrasmall-field component, which is observed both for MR and MEL [17, 19]. Furthermore, the ultrasmall-field component is shown to be a result of the spin's coherent motion while the saturation behavior survives the loss of spin coherence. The isotope effect obtained from this mechanism by replacing the spin-$\frac{1}{2}$ protons with the spin-1 deuterons is in satisfying agreement with experimental results.

Firstly, we illustrate how the motion of the carrier's spin could influence the incoherent CT rate. A two-site model with site i and j is taken for convenience, and the carrier is initially localized on site i. Once on the site, the carrier's spin will inevitably interact with some local degree of freedom, which consists of the local environment of spin (LES). This mutual interaction will bring the composite system of both the carrier's spin and LES into entangled states. The entanglement is present both for the case of dynamic evolution, and for the case of the composite system relaxing to thermal equilibrium. Concurrent with the interaction concerning the carrier's spin is the interaction between the carrier and the lattice vibrations, which offers the energy for the CT to site j with different electronic energy. The whole CT process is incoherent due to the small relaxation time of the lattice vibrations which are on the order of picoseconds [20]. In terms of the density operator $\hat{\rho}$ of the two-site system, the incoherentness is reflected by the quick vanishing of the off-diagonal matrix elements ρ_{ij} $(\equiv \langle i|\,\hat{\rho}\,|j\rangle)$. The incoherent CT process also have substantial influence on the final state of the carrier's spin after the CT. As the interactions between the carrier and the lattice vibrations are not spin-specific, the coherence within the subspace of the the carrier's spin should remain intact to these interactions leading to fast decoherence. However, as the coherence between the site i and site j is lost after the incoherent CT, the entanglement between the carrier's spin (now on site j) and the LES on site i, as a sign of the nonlocal quantum coherence, is expected to be terminated [21]. The above two requirements can be achieved by an adiabatic elimination procedure. If the initial state of the composite system for the CT is designated as ρ_i, the density matrix for the carrier's spin/the LES after the CT is $\rho_{s/e} = \mathrm{tr}_{e/s}\{\rho_i\}$, where $\mathrm{tr}_{e/s}$ denotes the partial trace over the degrees of freedom of the LES/the carrier's spin. The final unentangled state ρ_f can be written as a direct product of the states ρ_s and ρ_e. By a generalization of the Fermi golden rule, the contribution to the CT rate from this disentanglement process can be incorporated in a quantity η, which reads

$$\eta = \mathrm{tr}\{\rho_i\rho_f\} = \mathrm{tr}\{\rho_i(\rho_s \otimes \rho_e)\}. \tag{1}$$

To show the physical meaning of η more clearly, we suppose the initial state ρ_i is a pure state, which can be written as $\rho_i = |\phi_i\rangle\langle\phi_i|$, with

$$|\phi_i\rangle = c_+\left|\frac{1}{2}\right\rangle|e_+\rangle + c_-\left|-\frac{1}{2}\right\rangle|e_-\rangle, \tag{2}$$

where $|e_+\rangle$ and $|e_-\rangle$ are the states of the LES of site i, that are correlated with the states of the carrier's spin with magnetic quantum number $m_s = \frac{1}{2}$ and $m_s = -\frac{1}{2}$; c_+ and c_- are the corresponding superposition coefficients. In this case, η can be simplified to

$$\eta = 1 - 3|c_+|^2|c_-|^2\left(1 - |\langle e_+|\, e_-\rangle|^2\right), \tag{3}$$

which is directly related to the degree of entanglement between the carrier's spin and the LES on site i in the initial state . If the contributions from other parts are denoted by ν_0, the complete form of CT rate can be written as $\nu_0\eta$. It should be noted that, besides the details of the electronic states and the interaction with lattice vibrations, the value of ν_0 also depends on whether site j has already been occupied by a carrier, as well as the spin states, which has been considered by several papers [15, 22]. Here we focus on the influence of η, originating from the disentanglement between the carrier's spin and the LES of site i. An external magnetic field will alter the entanglement between the carrier's spin and the LES, which leads to a magnetic-field modulation mechanism.

A further issue needs to be addressed if the motion of the carrier's spin is treated as coherent, in which case the composite system evolves with time, and thus the CT rate, *i.e.*, $\eta \equiv \eta(t)$ from $\rho_i \equiv \rho_i(t)$. To reach a time-independent quantity for the effective rate, we treat the CT process as Markovian. Suppose the probability that the carrier is still on site i at time t is designated as $P(t)$, the equation for $P(t)$ is $\mathrm{d}P(t)/\mathrm{d}t = -\nu_0\eta(t)P(t)$. The average waiting time for the carrier on site i is

$$\langle t_w\rangle = \int_0^\infty \exp\left(-\nu_0\int_0^t \eta(\tau)\mathrm{d}\tau\right)\mathrm{d}t. \tag{4}$$

If the contribution from the present mechanism is neglected, $\eta(t) \equiv 1$, $\nu_0 \equiv 1/\langle t_w\rangle$. Similarly, an equivalent quantity $\nu = 1/\langle t_w\rangle$ can be defined as the effective CT rate when $\eta(t)$ is incorporated.

To present the theory quantitatively, we consider a basic CT process, which is a charge carrier hopping from a site i to its neighboring vacant site j. This process could influence both the charge transport and the electroluminescence. We take a hyperfine interaction model for the coupling between the carrier's spin and the LES, which is [19]

$$H_s = \sum_\alpha J_\alpha \mathbf{I}_\alpha \cdot \mathbf{s} + g\mu_B B s_z, \tag{5}$$

where we have set $\hbar = 1$; α is the label for the different constituents of the LES, with J_α the corresponding coupling strength and $\mathbf{I}_\alpha$ the nuclear spin operators; $\mathbf{s}$ are the carrier's spin operators; g is the Landé factor which is taken to be 2; μ_B is the Bohr magneton. The magnetic field B is chosen to be along the z-axis without loss of generality. The main result is shown in Fig. 1, where the relative change of the hopping rate with the magnetic field is $\Delta\nu/\nu \equiv [\nu(B) - \nu(0)]/\nu(0)$. In the calculation, we have taken one spin-$\frac{1}{2}$ mode as the LES and set $\nu_0 = 3.5J$. The final result is an average over



FIG. 1: The magnetic-field dependence of hopping rate $\Delta\nu/\nu$ with $\nu_0 = 3.5J$. The dashed line is the fit by a Lorentzian lineshape for the saturation component, with $B_{1/2}$ the half-width at half-maximum (HWHM). The inset shows the ultrasmall-field component of $\Delta\nu/\nu$, where B_m is the magnetic field under which the hopping rate reaches its minimum value.



FIG. 2: The ν_0-dependence of the characteristics of the magnetic-field dependent $\Delta\nu/\nu$. The variation of the saturation value $(\Delta\nu/\nu)_\mathrm{sat}$ and the minimum value $(\Delta\nu/\nu)_\mathrm{min}$ with ν_0 are shown in (a); the variation of the HWHM $B_{1/2}$ is shown in (b) and the variation of the magnetic field under which the hopping rate reaches its minimum value B_m is shown in (c). The data of B_m has been multiplied by 10 for clarity.

all the initial states, with the carrier's spin taking any orientation and the LES in any of its eigenstates in the external magnetic field. Two components are present in the magnetic-field dependence of the effective hopping rate ν: a saturation component at large magnetic fields which can be fitted well by a Lorentzian-like lineshape $B^2/(B^2+B_{1/2}^2)$, together with a negative ultrasmall-field component. This result is in good agreement with the experimental observations for MR [17], as well as MEL [19]. We emphasize that this kind of magnetic-field dependence is the general outcome of our theory, which does not depend on the choice of parameters. For example, we show in Fig. 2 the variation of the characteristics of this magnetic-field dependence with ν_0. Four quantities are calculated, including the saturation amplitude $(\Delta\nu/\nu)_\mathrm{max}$, the half-width at half-maximum (HWHM) $B_{1/2}$, the minimum value of the ultrasmall-field component $(\Delta\nu/\nu)_\mathrm{min}$ and the corresponding magnetic field B_m. When ν_0 increases, the integrand of Eq. (4) decays more quickly and there is less time to build up the entanglement, so both $(\Delta\nu/\nu)_\mathrm{sat}$ and $(\Delta\nu/\nu)_\mathrm{min}$ decreases. The ultrasmall-field component vanishes for ν_0 beyond about $5J$, because this component is from the oscillation behavior of the entanglement, which will not take effect for large ν_0. Furthermore, while B_m remains nearly unchanged, $B_{1/2}$ increases steadily with ν_0. We also point out that the two-component magnetic-field dependence of $\Delta\nu/\nu$ persists when more spin-$\frac{1}{2}$ modes are included as the LES, only with quantitative modifications of the above quantities. The results for the case of two uncorrelated spin$-\frac{1}{2}$ modes as the LES are shown in the supplementary material [23].

The two-component magnetic-field dependence can be understood through some analytical results. We consider four basic initial states $|a,b\rangle$, with $a,b=\pm\frac{1}{2}$, in which a for the carrier's spin and b is for the LES. Other initial states can be seen as a proper superposition of the four, so the situation of the four could reflect qualitatively the behavior of Fig. 1 from detailed averaging procedures. With the hyperfine-interaction Hamiltonian of Eq. (5), the total spin in the z direction, $S_z = I_z + s_z$, is conserved, and we can classify the initial states by this quantity. Both the initial states of $\left|\frac{1}{2},\frac{1}{2}\right\rangle$ $(S_z=1)$ and $\left|-\frac{1}{2},-\frac{1}{2}\right\rangle$ $(S_z=-1)$ are eigenstates without entanglement, giving $\eta(t)=1$. However, the other two initial states $\left|-\frac{1}{2},\frac{1}{2}\right\rangle$ and $\left|\frac{1}{2},-\frac{1}{2}\right\rangle$ $(S_z=0)$ become entangled states evolving with time, giving the same nontrivial result

$$\eta(t) = 1 - \frac{3}{4}\cdot\frac{\sin^2\omega t + 2\alpha^2(1-\cos\omega t)}{(1+\alpha^2)^2}, \tag{6}$$

where $\omega = J\sqrt{1+\alpha^2}$ and $\alpha \equiv g\mu_B B/J$. A time-independent quantity can be got by taking the time-average, which is

$$\bar{\eta}(B) = 1 + \frac{3}{5}\cdot\frac{\alpha^2(\alpha^2-2)}{(1+\alpha^2)^2} \tag{7}$$

where we have scaled the quantity so that $\bar{\eta}(B=0)=1$. This direct time-average corresponds to the situation when ν_0 is sufficiently small, and the waiting time is much longer than the oscillation period in $\eta(t)$. Eq. (7) is plotted in Fig. 3(a), and it is clear that $\bar{\eta}$ is less than 1 for $\alpha \le \sqrt{2}$, which gives the negative ultrasmall-field component, and saturates for large B. This behavior can be traced back to the two-fold role of the increasing Zeeman splitting with the magnetic field on the entanglement. For example, for the initial state $\left|\frac{1}{2},-\frac{1}{2}\right\rangle$, with magnetic field being zero, the initial state could evolve to the unentangled state $\left|-\frac{1}{2},\frac{1}{2}\right\rangle$ halfway in a complete period; with small magnetic fields, the degeneracy between the two untangled states is lifted, and the system remains entangled; with sufficiently large magnetic fields, the energy cost of flipping the carrier's spin allows no sizable probability amplitude of $\left|-\frac{1}{2},\frac{1}{2}\right\rangle$. The entanglement remains small and the hopping ability becomes larger.



FIG. 3: (a) The magnetic-field dependence of the time-averaged $\bar{\eta}(B)$ for each one of the four states ($|a,b\rangle$, $a,b=\pm\frac{1}{2}$) as the initial state. The result of the $S_z=0$ states show both the negative ultrasmall-field component and the saturation component at large magnetic field; (b) The magnetic field dependence of $\bar{\eta}(B)$ for the eigenstates of the hyperfine-interaction Hamiltonian, which only shows the saturation component at large magnetic field without the ultrasmall-field component.

Till now, we have been considering the situation of the coherent spin motion on the initial site i. However, it should be noted that in some cases the coherency might be disturbed, such as when the spin-orbit interaction is enhanced by doping transition metal complex [24]. Although the interaction becomes more complicated, the results based on the hyperfine-interaction model of Eq. (5) might still be indicative. In Fig. 3(b), the magnetic-field dependent $\bar{\eta}(B)$ is shown for the eigenstates of the Hamiltonian of the composite system consisting of the carrier's spin and the LES, which are the states when the composite system reaches thermal equilibrium. Similar to the previous situation, two of the four eigenstates, which are $\left|\frac{1}{2},\frac{1}{2}\right\rangle$ and $\left|-\frac{1}{2},-\frac{1}{2}\right\rangle$ with $S_z=\pm1$, are unentangled states with $\eta(B)=1$. The remaining two eigenstates with $S_z=0$ are entangled ones with

$$\bar{\eta}(B)=1+\frac{3\alpha^2}{1+\alpha^2}. \tag{8}$$

It can be seen that the ultrasmall-field component is not present, in contrast to the results for coherent spin motion, while the saturation component survives the loss of spin coherence. This implies that the ultrasmall-field component observed in experiments could be a sign of the spin coherency. The persistence of the saturation component might also explain why the magnetic-field effect is still observed in the devices made by hydroxyquinolates consisting of heavy metal atoms [25].

We further calculate the isotope effect of the magnetic-field dependence of the hopping rate, by replacing the spin$-\frac{1}{2}$ protons by the spin-1 deuterons, and the result is shown Fig. 4. The coupling strength for the spin-1 case is chosen to be $0.5J$, where J is that of the spin$-\frac{1}{2}$ case, as the mass of deuterons are twice that of ordinary hydrogen atoms. The resulting HWHM of the spin-1 case is larger than that of the spin$-1/2$ case. Furthermore, only a tiny ultrasmall-field component is present for the spin-1 case, which is shown more clearly in the inset. The reason behind the difference can be understood by similar analysis as above, which is presented in the supplementary material [23]. Without any further assumption, the results obtained here is in excellent agreement with the isotope effect of MEL observed experimentally [19].



FIG. 4: The isotope effect obtained by replacing the spin$-\frac{1}{2}$ proton with the spin-1 deuteron as the LES. The behavior at ultrasmall magnetic field is shown in the inset. Compared with the spin$-\frac{1}{2}$ case, the ultrasmall-field component for the spin-1 case becomes almost flat.

Finally, we would like to emphasize that this work aims to present a general microscopic mechanism describing how the incoherent CT processes themselves are influenced by the carrier's spin states. With this mechanism, we can understand the peculiar properties of the MR and MEL observed for many different organic materials. Quantitative comparison with specific experimental curves is beyond the scope of this paper and could be reached by considering specific materials as well as the working conditions. Besides the hyperfine-interaction model, this mechanism can be applied to other CT processes depending on which process is dominant in the specific organic devices. In some cases, there might exist more than one dominant CT process, when the magnetic-field effect should display multiple Lorentzian-shape components. This kind of behavior has actually been concluded by the careful analysis of experimental data [26].

In summary, we have proven that the entanglement between the carrier's spin and the local environment contributes a factor to the incoherent CT rate. This offers a general magnetic-field modulation mechanism, which leads to the MR in organic semiconductors. For the hopping of a single carrier to a vacant site, by considering a hyperfine-interaction model, both the saturation component and the negative ultrasmall-field component emerge naturally. The mechanism holds promise for the incorporation of other influential CT processes leading towards a more comprehensive understanding of the magnetic-field effect in organic materials.

The authors would like to thank V. Dediu, A. J.

Drew, W. P. Gillin, D.-H. Lee, L. Yu, and T. Yu for their helpful discussions and M. Willis for the reading of this manuscript. We acknowledge the financial supports from the National Natural Science Foundation of China and the National Basic Research Program of China (2012CB921401 and 2009CB929204).

---

* Email: cqw@fudan.edu.cn

[1] E. Collini, C. Y. Wong, K. E. Wilk, P. M. G. Curmi, P. Brumer, and G. D. Scholes, Nature **463**, 644 (2010).

[2] M. Sarovar, A. Ishizaki, G. R. Fleming, and K. B. Whaley, Nature Phys. **6**, 462 (2010).

[3] F. Galve, L. A. Pachon, and D. Zueco, Phys. Rev. Lett. **105**, 180501 (2010).

[4] M. E. Gershenson, V. Podzorov and A. F. Morpurgo, Rev. Mod. Phys. **78**, 973 (2006).

[5] A. Miller and E. Abrahams, Phys. Rev. **120**, 745 (1960).

[6] R. A. Marcus, J. Chem. Phys. **43**, 679 (1965).

[7] H. Bässler, Phys. Status Solidi B **175**, 15 (1993).

[8] O. Rubel, S. D. Baranovskii, W. Stolz, and F. Gebhard, Phys. Rev. Lett. **100**, 196602 (2008).

[9] J. Kalinowski, M. Cocchi, D. Virgili, P. D. Marco, and V. Fattori, Chem. Phys. Lett. **380**, 710 (2003).

[10] T. L. Francis, O. Mermer, G. Veeraraghavan, and M. Wohlgenannt, New J. Phys. **6**, 185 (2004).

[11] P. A. Bobbert, W. Wagemans, F. W. A. van Oost, B. Koopmans, and M. Wohlgenannt, Phys. Rev. Lett. **102**, 156604 (2009).

[12] D. R. Mccamey, H. A. Seipel, S.-Y. Paik, M. J. Walter, N. J. Borys, J. M. Lupton, and C. Boehme, Nature Mater. **7**, 723 (2008).

[13] B. R. Gautam, T. D. Nguyen, E. Ehrenfreund, and Z. V. Vardeny, Phys. Rev. B **85**, 205207 (2012).

[14] F. L. Bloom, M. Kemerink, W. Wagemans, and B. Koopmans, Phys. Rev. Lett. **103**, 066601 (2009).

[15] S. P. Kersten, A. J. Schellekens, B. Koopmans, and P. A. Bobbert, Phys. Rev. Lett. **106**, 197402 (2011).

[16] J. D. Bergeson, V. N. Prigodin, D. M. Lincoln, and A. J. Epstein, Phys. Rev. Lett. **100**, 067201 (2008).

[17] T. D. Nguyen, B. R. Gautam, E. Ehrenfreund, and Z. V. Vardeny, Phys. Rev. Lett. **105**, 166804 (2010).

[18] Y. Zhang, R. Liu, Y. L. Lei, and Z. H. Xiong, Appl. Phys. Lett. **94**, 083307 (2009).

[19] T. D. Nguyen, G. Hukic-Markosian, F. Wang, L. Wojcik, X.-G. Li, E. Ehrenfreund, and Z. V. Vardeny, Nature Mater. **9**, 345 (2010).

[20] A. Troisi and G. Orlandi, Phys. Rev. Lett. **96**, 086601 (2006).

[21] The relation between entanglement and coherence has been studied widely, especially that between the nonlocal entanglement and local coherence, with the phenomenon of entanglement sudden death. See T. Yu, and J. H. Eberly, Phys. Rev. Lett. **93**, 140404 (2004); **97**, 140403 (2006); Phys. Rev. B **68**, 165322 (2003); Science **323**, 598 (2009). Here, we concern the relation between the nonlocal coherence and nonlocal entanglement, that are much more correlated.

[22] P. A. Bobbert, T. D. Nguyen, F. W. A. van Oost, B. Koopmans, and M. Wohlgenannt, Phys. Rev. Lett. **99**, 216801 (2007).

[23] See the supplementary material of this Letter.

[24] V. N. Prigodin, J. D. Bergeson, D. M. Lincoln, A. J. Epstein, Synth. Met. **156**, 757 (2008).

[25] P. Shakya, P. Desai, M. Somerton, G. Gannaway, T. Kreouzis, and W. P. Gillin, J. Appl. Phys. **103**, 103715 (2008).

[26] W. P. Gillin, S. Zhang, N. J. Rolfe, P. Desai, P. Shakya, A. J. Drew, and T. Kreouzis Phys. Rev. B **82**, 195208 (2010).